

Microwave & RF Materials Guide









Advanced Materials for the Designs of Tomorrow

www.atechcircuit.com

RF & Microwave Materials Guide

Arlon Microwave Materials specializes in products made from fluoropolymers (i.e. PTFE), ceramic filled fluoropolymers, ceramic-filled hydrocarbon thermosets, and other materials that deliver the electrical performance needed in frequency-dependent circuit applications. These products are supplied as copper-clad laminates with bonding plies, or prepregs, for production of multilayer printed circuits. Arlon has over 55 years of experience in microwave materials, today providing products that are used to make combiner boards and feed networks for microwave applications as well as base station antennas and power amplifier boards for the wireless telecommunications infrastructure market.

Our facilities in California, Delaware and China employ state-of-the-art production equipment, engineered to provide cost-effective, flexible manufacturing capacity to permit quick response to customer requirements while meeting the most stringent quality and tolerance demands. All of our manufacturing sites are ISO 9001: 2008 registered, and through rigorous quality control practices and commitment to continuous improvement, we are dedicated to meeting and exceeding our customer's requirements.

To better service our global customer base, Arlon created the venture, Arlon Material Technologies Co, Ltd. in Suzhou, Jiangsu Province, China. This venture includes both a Finishing Center and a manufacturing facility. The finishing center is located in Suzhou and has been operational since mid-2004. The Manufacturing Facility opened in October 2006. This facility contains a new, State-of-the-art vacuum press that has capability to laminate both High Temperature PTFE Microwave Laminates, High Performance Polyimide, and Low-loss Thermoset Based Substrates. This facility is equipped with the highest degree of process control in the industry.

A lower cost, higher performance, series of products lower loss have been launched in the 2.50 to 3.50 range. The AD "A" Series includes AD255A, AD260A, AD300A and others. These microwave Laminates utilize ceramic technologies to reduce loss and tighten tolerances. They are well suited for Base Station Antennas, Satellite Radio Antennas and Power Amplifiers where low loss is critical. These products are a significant improvement in cost/performance over traditional PTFE/Glass based laminates, As further cost/performance improvement over AD "A" products, AD "C" series are the third generation commercial laminate materials, designed with enhanced mechanical and electrical performance for today's telecommunication infrastructure.

One of our most exciting products is a lower loss version of CLTE, called CLTE-XT. CLTE-XT has the lowest loss, lowest thermal expansion, highest phase stability, and lowest moisture absorption of any product in its class. It is truly "Best-in-Class." Further innovations in new low loss materials are also targeted in the near future and Arlon remains committed to the development of advanced materials targeted for high performance circuit boards and electronics.

Arlon maintains a significant commitment to research & development. Exciting recent products include the Thermally Conductive PTFE-based laminates, TC600 and TC350. These materials provide "Best-in-Class" Thermal Conductivity (W/mk) for applications where temperature extremes are normal and Heat Rejection is a Primary Consideration. These materials lower junction temperatures for Improved Power Amplifier Reliability and pull heat away from critical solder joints that can fatigue through cycling. TC600 and TC350 also offer greater Thermal Phase Stability for applications that are cycled and still need to maintain tight dielectric constant tolerances for phase sensitive circuitry.

RF & Microwave Materials Guide

This guide covers typical properties for a wide variety of Arlon's microwave material products, ranging from our high performance PTFE laminates to our cost-optimized PTFE and non-PTFE based RF laminates and composites. Although a comprehensive summary of Arlon's capabilities and full product-line is not feasible, this guide provides a good overview of the core microwave material products that Arlon produces and covers typical properties as well as the wide variety of standard product options in laminate thicknesses and nominal dielectric constants. To reduce complexity and confusion, the following information represents the standard and common items.

Please contact Customer Service if you do not see your desired thickness or dielectric constant or require additional assistance. For more detail on a specific product, please refer to the product specific datasheet available on-line at www.arlon-med.com.

Table of Contents	
Product Overview	3-4
CLTE-XT, CLTE-AT, CLTE	5
TC Series (Thermally Conductive)	6
AD "C" Series (Third generation of AD Series)	6
AD "A" Series (Improvements on AD Series)	7
Higher Dielectric Constant (4.10 to 11)	8
AD Series	9
DiClad	10
CuClad	11
IsoClad	12
AR Series	13
Low Loss Thermosets - 25N, 25FR, Multiclad HF	13
Copper Cladding	14
Arlon Part Numbers	15
Customer Service/Sales Contact Information	Back

Properties listed in this guide are for reference purposes only and are subject to change without notice; they are not to be used as specification limits. This information creates no expressed or implied warranties. The properties of Arlon laminates may vary depending on the design and application.



Product Overview

Product		Dielectric	Dissipation	Thermal Coefficient	Coefficient	of The
Product Composition	© 10 GHz	Factor @ 10 GHz	of Er ppm/°C	x	Y	
CLTE-XT. CLTE	-AT and CLTE High Performance, Excellent	Dielectric Constan	t Control and Phase	Stability with Temp	perature	
CLTE-XT	Glass, PTFE and Micro-Dispersed Ceramic	2.94*	0.0012	-9	8	8
CLTE-AT	Glass, PTFE and Micro-Dispersed Ceramic	3.00	0.0013	-10	8	8
CLTE	Glass, PTFE and Micro-Dispersed Ceramic	2.98*	0.0023*	-9	10	12
High Thermal (I Conductivity, Excellent Dielectric Constant C	ontrol and Phase S	Stability with Tempe	rature		
TC350	Glass, PTFE and Micro-Dispersed Ceramic	3.50	0.0020	-9	7	7
TC600	Glass, PTFE and Micro-Dispersed Ceramic	6.15	0.0020	-75	9	9
AD "C" Series	- Enhanced next generation of AD "A" Series	s. Woven Glass, PT	FE and Micro-Dispe	ersed Ceramic		
AD250C	Glass, PTFE and Micro-Dispersed Ceramic	2.50	0.0014	-75	16	16
AD255C	Glass, PTFE and Micro-Dispersed Ceramic	2.55	0.0014	-75	16	16
AD300C	Glass, PTFE and Micro-Dispersed Ceramic	2.97	0.0020	-25	12	12
AD "A" Series -	- Lower Loss and Improved Performance ov	er Traditional AD S	eries. Woven Glass,	PTFE and Micro-Di	ispersed Ceramic	
AD255A	Glass, PTFE and Micro-Dispersed Ceramic	2.55	0.0015	-138	16	16
AD260A	Glass, PTFE and Micro-Dispersed Ceramic	2.60	0.0017	-80	16	16
AD300A	Glass, PTFE and Micro-Dispersed Ceramic	3.00	0.0020	-110	12	12
AD320A	Glass, PTFE and Micro-Dispersed Ceramic	3.20	0.0032	-125	14	14
AD350A	Glass, PTFE and Micro-Dispersed Ceramic	3.50	0.0030	-55	5	9
High Dielectric	Constant for Circuit Militarization & Patch A	Intenna Applicatio	ns			
AD410	Glass, PTFE and Micro-Dispersed Ceramic	4.10	0.0030	-55	9	9
AD430	Glass, PTFE and Micro-Dispersed Ceramic	4.30	0.0030	-55	9	9
AD450A	Glass, PTFE & Ceramic, 0.120" Thick	4.50	0.0030	-200	10	10
AD600	Glass, PTFE and Micro-Dispersed Ceramic	6.15*	0.0030	-241	11	10
AD1000	Glass, PTFE and Micro-Dispersed Ceramic	10.20*	0.0023	-380	8	10
Traditional - Hi	ghest Performance. PTFE Coated Light Wov	en Glass Styles, In	terdispersed PTFE f	ilms		
DiClad 522	Woven Fiberglass reinforced PTFE	2.40 - 2.60*	0.0018	-153	14	2
DiClad 527	Woven Fiberglass reinforced PTFE	2.40 - 2.60*	0.0018	-153	14	2
DiClad 870	Woven Fiberglass reinforced PTFE	2.33	0.0013	-161	17	2
DiClad 880	Woven Fiberglass reinforced PTFE	2.17, 2.20	0.0009	-160	25	34
CuClad 250GT	Cross Plied Woven Fiberglass rinforced PTFE	2.50	0.0018	-170	18	1:
CuClad 250GX	Cross Plied Woven Fiberglass rinforced PTFE	2.40 - 2.55*	0.0018	-170	18	1:
CuClad 233LX	Cross Plied Woven Fiberglass rinforced PTFE	2.33	0.0013	-171	23	2
CuClad 217LX	Cross Plied Woven Fiberglass rinforced PTFE	2.17, 2.20	0.0009	-151	29	2
IsoClad 933	Non-Woven Fiberglass reinforced PTFE	2.33	0.0016	-132	31	3
IsoClad 917	Non-Woven Fiberglass reinforced PTFE	2.17	0.0013	-157	46	4
	ries - Woven Glass and PTFE or Woven Glas	i e				
AD250	Woven Glass and PTFE	2.50	0.0018	-110	12	1:
AD255	Woven Glass and PTFE	2.55	0.0018	-110	12	1:
AD320	Glass, PTFE and Micro-Dispersed Ceramic	3.20	0.0038	-110	12	1
	gacy Product. Reference AD1000 as a Next (000	44	
	Glass, PTFE and Micro-Dispersed Ceramic	10.00*	0.0030	-233	14	1
AR1000						
Low Loss Ther	moset Resin Systems - Multilayer Capable,		0.0005	07	4.5	
	moset Resin Systems - Multilayer Capable, Ceramic Hydrocarbon Ceramic Hydrocarbon	3.38 3.58	0.0025	-87 50	15 16	15

^{*} Refer to Tables for Dielectric Constant and Thickness Options.

Expansion	Typical Peel	Water	Specific	Conductivity		Thermal	
z	Strength (lbs)	Absorption (%)	Gravity			Volatile	Flammability UL Rating
	•			•			
00	7.0	0.00	0.00	0.50	0.00	0.00	111.04.1/0
20 20	7.2 6.5	0.02	2.02 2.06	0.56 0.64	0.02 0.02	0.00	UL94-V0 UL94-V0
34	7	0.03	2.38	0.64	0.02	0.00	UL94-V0
04	,	0.04	2.00	0.00	0.02	0.00	0234 V0
23	7	0.05	2.30	1.03	0.02	0.01	UL94-V0
35	8	0.03	3.20	1.1(z), 1.4(x,y)	0.02	0.00	UL94-V0
50	12	0.04	2.30	0.30	NT	NT	N/A
50	12	0.04	2.30	0.30	NT	NT	UL94-V0
50	13	0.05	2.10	0.45	NT	NT	UL94-V0
80	12	0.04	2.30	0.28	NT	NT	UL94-V0
80	17	0.04	2.30	0.30	NT	NT	UL94-V0
125	13	0.02	2.10	0.32	NT	NT	UL94-V0
128	14	0.02	2.09	0.49	NT	NT	UL94-V0
35	17	0.1	2.10	0.45	NT	NT	UL94-V0
				0.45	0.02	0.02	UL94-V0
40	17	0.06	2.10	0.46	NT	NT	UL94-V0
40	17	0.06	2.10	0.46	NT	NT	UL94-V0
40	12	0.06	2.50	0.40	NT	NT	UL94-V0
45	12	0.04	2.45	0.46	0.02	0.01	UL94-V0
20	> 12	0.03	3.2	0.81	0.01	0.00	UL94-V0
173	14	0.03	2.31	0.254	0.02	0.00	UL94-V0
173	14	0.03	2.31	0.254	0.02	0.00	UL94-V0
217	14	0.02	2.26	0.257	0.02	0.00	UL94-V0
252	14	0.02	2.23	0.261	0.01	0.01	UL94-V0
177	14	0.03	2.31	0.254	0.01	0.00	UL94-V0
177	14	0.03	2.31	0.254	0.01	0.00	UL94-V0
194	14	0.02	2.26	0.258	0.01	0.01	UL94-V0
246	14	0.02	2.23	0.261	0.01	0.01	UL94-V0
203	10	0.05	2.27	0.263	0.03	0.00	UL94-V0
236	10	0.04	2.23	0.263	0.02	0.00	UL94-V0
05	4.4	0.07	0.40	0.005	NIT	NIT	111.04.1/0
95 95	14	0.07	2.40	0.235	NT NT	NT NT	UL94-V0
95 95	14 17	0.07 0.06	2.40 2.40	0.235 0.235	NT NT	NT NT	UL94-V0 UL94-V0
37	5	0.08	2.84	0.645	0.02	0.00	UL94-V0
52	5	0.09	1.70	0.45	0.17	0.01	N/A
52 59	5	0.09					UL94-V0
20	9	0.10	1.80 V V.70	atech		l1toCO	111 UL94-V0
]	I	1	* * * ***	1000011			

CLTE-XT, CLTE-AT and CLTE

CLTE-XT is the next generation of CLTE with "Best-In-Class" Loss Tangent and Lowest Insertion loss in its class. Excellent dimensional stability, Phase Stability and CTE performance.

CLTE-AT is commercially priced product. It uses common technologies developed for CLTE-XT, and with some changes to make the product more affordable, but with less stringent tolerances. To maintain its lower cost base, CLTE-AT has less options for copper style and panel sizes.

CLTE is Glass/PTFE/micro-dispersed ceramic laminates. Offers superior thermomechanical (CTE) stability and Dk over temperature with best-in-class processibility for a PTFE-based laminate.

	St	andard Thickr	Dielectric Constant		
Product	Inches	Millimeters	Tolerance	Nominal	Tolerance
	0.0051	0.130	±0.0005	2.79	±0.03
	0.0094	0.239	±0.0007	2.89	±0.03
	0.0145	0.369	±0.001	2.94	±0.03
	0.020	0.508	±0.001	2.92	±0.03
	0.025	0.635	±0.001	2.94	±0.03
CLTE-XT	0.030	0.762	±0.001	2.94	±0.03
Master Sheet Size**	0.040	1.016	±0.002	2.94	±0.03
36" x 48"	0.045	1.143	±0.002	2.94	±0.03
	0.048	1.219	±0.0024	2.95	±0.03
	0.059	1.499	±0.002	2.95	±0.03
	0.060	1.524	±0.002	2.94	±0.03
	0.070	1.778	±0.003	2.95	±0.03
	0.090	2.286	±0.005	2.95	±0.03
	0.100	2.540	±0.003	3.01	±0.03
	0.005	0.127	±0.0005	3.00	±0.04
	0.010	0.254	±0.0007	3.00	±0.04
	0.015	0.381	±0.001	3.00	±0.04
	0.020	0.508	±0.0015	3.00	±0.04
	0.025	0.635	±0.002	3.00	±0.04
CLTE-AT	0.030	0.762	±0.002	3.00	±0.04
Master Sheet Size**	0.040	1.016	±0.0025	3.00	±0.04
36" x 48"	0.050	1.270	±0.0025	3.00	±0.04
	0.060	1.524	±0.003	3.00	±0.04
	0.090	2.286	±0.005	3.02	±0.04
	0.125	3.175	±0.006	3.02	±0.04
	0.003	0.076	±0.0005	2.75	±0.08
	0.0053	0.135	±0.0005	2.85	±0.06
	0.010	0.254	±0.001	2.94	±0.06
	0.015	0.381	±0.0015	2.95	±0.04
CLTE	0.020	0.508	±0.002	2.96	±0.04
	0.024	0.610	±0.002	2.97	±0.04
Master Sheet Size** 36" x 48"	0.031	0.787	±0.002	2.98	±0.04
	0.040	1.016	±0.003	2.98	±0.04
	0.047	1.194	±0.003	2.98	±0.04
	0.062	1.575	±0.004	2.98	±0.04
	0.093	1 2.362	• _±0.005	2.98	±0.04

**Master Sheet Sizes are not available on all products of thicknesses. Tolerances are subject to change and custom tolerances may be available. Please contact Arlon Customer Service with questions about material availability.

TC Series

TC350 and TC600 offer "Best-In-Class" Thermal Conductivity and Dielectric Constant Stability with Temperature leading to excellent impedance control and electrical phase stability. Excellent thermomechanical (CTE) stability for highly reliability plated thru holes and component attachment.

Product	St	andard Thickr	Dielectric Constant		
Product	Inches	Millimeters	Tolerance	Nominal	Tolerance
	0.005	0.127	±0.0005	3.50	±0.05
	0.010	0.254	±0.0007	3.50	±0.05
	0.015	0.381	±0.001	3.50	±0.05
	0.020	0.508	±0.0015	3.50	±0.05
	0.025	0.635	±0.002	3.50	±0.05
TC350	0.030	0.762	±0.002	3.50	±0.05
Master Sheet Size**	0.040	1.016	±0.003	3.50	±0.05
36" x 48"	0.050	1.270	±0.003	3.50	±0.05
	0.060	1.524	±0.003	3.50	±0.05
	0.090	2.286	±0.004	3.50	±0.05
	0.100	2.540	±0.005	3.50	±0.05
	0.120	3.048	±0.008	3.50	±0.05
	0.125	3.175	±0.008	3.50	±0.05
	0.250	6.350	±0.012	3.50	±0.05
	0.010	0.254	±0.0007	6.15	±0.15
	0.015	0.381	±0.001	6.15	±0.15
	0.020	0.508	±0.001	6.15	±0.15
	0.025	0.635	±0.0015	6.15	±0.15
	0.030	0.162	±0.002	6.15	±0.15
TC600	0.035	0.889	±0.002	6.15	±0.15
Master Sheet Size**	0.040	1.016	±0.002	6.15	±0.15
36" x 48"	0.050	1.270	±0.002	6.15	±0.15
	0.060	1.524	±0.003	6.15	±0.15
	0.090	2.286	±0.004	6.15	±0.15
	0.125	3.175	±0.004	6.15	±0.15
	0.250	6.350	±0.008	6.15	±0.15

^{*}Master Sheet Sizes are not available on all products or thicknesses. Tolerances are subject to change and custom tolerances may be available. Please contact Arlon Customer Service with questions about material availability.

AD "C" Series

Enhanced next generation products of AD "A" Series in terms of cost, mechanical and electrical performances, such as lower loss tangent, lower thermal expansion (CTE) and lower TCEr (for better phase stability), and improved passive intermodulation (PIM) performance.

Product**	St	andard Thickr	Dielectric Constant		
Product**	Inches	Millimeters	Tolerance	Nominal	Tolerance
_	0.020	0.508	±0.002	2.50	±0.04
AD250C	0.030	0.762	±0.002	2.50	±0.04
	0.060	1.524	±0.003	2.50	±0.04
AD255C	0.030	0.762	±0.002	2.55	±0.04
AD255C	0.060	1.524	±0.002	2.55	±0.04
AD0000 11/11	0.030	0.762	±0.002	2.97	±0.05
AD300C WW	W0.060 C	CII4.524 CU	$11_{\pm 0.002}$	2.97	±0.05

^{**}Master Sheet Size of 48" x 54", other DK, thickness options available. Tolerances are subject to change and custom tolerances may be available. Please contact Arlon Customer Service with questions about material availability.

AD "A" Series

Advancements and improvements to the original AD Series, low cost commercial laminates. Lower loss tangent, tighter dielectric and thickness tolerances, and PIM+ design offerings.

Product**	St	andard Thickr	Dielectric Constant		
Product**	Inches	Millimeters	Tolerance	Nominal	Tolerance
AD255A	0.030	0.762	±0.002	2.55	±0.04
(AD255C provides	0.031	0.787	±0.003	2.55	±0.04
lower cost and better	0.060	1.524	±0.003	2.55	±0.04
performance)	0.062	1.575	±0.003	2 _x 55	±0.04
AD260A	0.090	2.286	±0.003	2.60	±0.04
AD260A	0.125	3.175	±0.006	2.60	±0.04
	0.020	0.508	±0.002	3.00	±0.04
	0.030	0.762	±0.002	3.00	±0.04
AD300A	0.040	1.016	±0.002	3.00	±0.04
(AD300C provides	0.060	1.524	±0.002	3.00	±0.04
lower cost and better performance)	0.090	2.286	±0.005	3.00	±0.04
performance	0.120	3.048	±0.006	3.00	±0.04
	0.125	3.175	±0.006	3.00	±0.04
	0.030	0.762	±0.002	3.20	±0.04
	0.040	1.016	±0.002	3.20	±0.04
AD320A	0.045	1.143	±0.003	3.20	±0.04
	0.062	1.575	±0.003	3.20	±0.04
	0.125	3.175	±0.006	3.20	±0.04
	0.020	0.508	±0.015	3.50	±0.05
	0.030	0.762	±0.002	3.50	±0.05
	0.040	1.016	±0.003	3.50	±0.05
AD350A	0.060	1.524	±0.003	3.50	±0.05
ADOUGA	0.090	2.286	±0.004	3.50	±0.05
	0.120	3.048	±0.008	3.50	±0.05
	0.125	3.175	±0.008	3.50	±0.05
	0.200	5.080	±0.012	3.50	±0.05

^{**} Master Sheet Size of 36" x 48" is standard. Other DK or thickness options available. Tolerances are subject to change and custom tolerances may be available. Please contact Arlon Customer Service with questions about material availability.

High Dielectric Constant

For Circuit Miniaturization & High Gain Patch Antenna Applications. Excellent for applications requiring low loss, a higher dielectric constant, as well as mechanical robustness capable of handling stress, vibration or drop tests. Much more durable than either Alumina or Ceramic loaded Hydrocarbons.

	St	andard Thickr	Dielectric Constant		
Product**	Inches	Millimeters	Tolerance	Nominal	Tolerance
	0.030	0.762	±0.002	4.10	±0.12
	0.062	1.575	±0.003	4.10	±0.12
AD410	0.075	1.905	±0.004	4.10	±0.12
AD410	0.120	3.048	±0.006	4.10	±0.12
	0.125	3.075	±0.006	4.06	±0.06
	0.250	6.350	±0.008	4.10	±0.12
AD430	0.030	0.762	±0.002	4.30	±0.06
AD430	0.125	3.175	±0.006	4.23	±0.06
	0.010	0.254	±0.001	4.50	±0.25
	0.020	0.508	±0.0015	4.50	±0.25
	0.030	0.762	±0.002	4.50	±0.25
AD450	0.040	1.016	±0.003	4.50	±0.25
AD-100	0.050	1.270	±0.003	4.50	±0.25
	0.060	1.524	±0.003	4.50	±0.25
	0.070	1.778	±0.004	4.50	±0.25
	0.090	2.286	±0.005	4.50	±0.25
	0.010	0.254	±0.001	6.15	±0.40
	0.020	0.508	±0.0015	6.15	±0.40
AD600	0.031	0.787	±0.002	6.15	±0.40, ±0.15
	0.062	1.575	±0.003	6.15	±0.40
	0.090	2.286	±0.005	6.15	±0.40
AD600A	0.250	6.350	±0.012	6.15	±0.15
	0.0105	0.267	±0.001	9.10	±0.35
	0.015	0.381	±0.0015	9.70	±0.35
	0.020	0.508	±0.002	10.0	±0.35
	0.025	0.635	±0.002	10.2	±0.35
454000	0.030	0.762	±0.002	10.35	±0.35
AD1000	0.050	1.270	±0.002	10.6	±0.35
	0.059	1.499	±0.003	10.7	±0.35
	0.127	3.226	±0.006	10.9	±0.35
	0.050	1.270	±0.002	10.2	±0.35
AD1000X	0.098	2.489	±0.005	10.2	±0.35
	0.125	3.175	±0.006	10.2	±0.35

^{**}Master Sheet Size of 36" x 48" is standard. Other thicknesses available. Tolerances are subject to change and custom tolerances may be available. Please contact Arlon Customer Service with questions about material availability.

AD Series

The original AD Series is designed for commercial applications relying on a thicker laminate that are driven by low cost. PIM design offerings. Typical applications include base station antennas and BSA feed networks. Through the use of thicker building blocks and thicker glass styles, lower costs are achieved through less labor and machine time.

	St	andard Thickr	Dielectric Constant		
Product**	Inches	Millimeters	Tolerance	Nominal	Tolerance
	0.015	0.381	±0.0015	2.50	±0.05
	0.020	0.508	±0.002	2.50	±0.05
AD250	0.031	0.787	±0.003	2.50	±0.05
	0.062	1.575	±0.003	2.50	±0.05
	0.090	2.286	±0.007	2.50	±0.05
	0.125	3.175	±0.009	2.50	±0.05
	0.020	0.508	±0.002	2.55	±0.05
	0.030	0.762	±0.003	2.55	±0.05
AD255	0.031	0.787	±0.003	2.55	±0.05
(check options with	0.040	1.016	±0.003	2.55	±0.05
AD255A and AD255C for lower loss tangent	0.060	1.524	±0.003	2.55	±0.05
and tighter tolerances)	0.062	1.575	±0.003	2.55	±0.05
	0.080	2.032	±0.004	2.55	±0.05
	0.120	3.048	±0.009	2.55	±0.05
	0.125	3.175	±0.009	2.55	±0.05
AD320	0.020	0.508	±0.002	3.20	±0.10
(AD320A offers lower	0.031	0.787	±0.002	3.20	±0.10
loss tangent and	0.062	1.575	±0.003	3.20	±0.10
tighter tolerances)	0.093	2.362	±0.007	3.20	±0.10

^{**}Master Sheet Size of 36" x 48" is standard. Tolerances are subject to change and custom tolerances may be available. Please contact Arlon Customer Service with questions about material availability.

DiClad® Series

Unidirectional woven fiberglass / PTFE laminates available in a range of Dk's (2.17 to 2.60) and low dielectric loss values (0.0009 to 0.0018). These products use finer glass styles for precision and have a very high degree of low loss PTFE.

		Standard TI	nickness	Dielectric Constant		
Product	Inches	Millimeters	Tolerance	Nominal	Tolerance	
	0.015	0.381	±0.0015	2.50, 2.55	±0.05	
	0.020	0.508	±0.002	2.50	±0.05	
DiClad 522	0.024	0.610	±0.002	2.50, 2.60	±0.05	
(Thickness listed includes	0.031	0.787	±0.002	2.45, 2.50, 2.55, 2.60	±0.05	
copper cladding)	0.047	1.194	±0.002	2.50, 2.55, 2.60	±0.05	
Master Sheet Size** :	0.062	1.575	±0.003	2.45, 2.50, 2.55, 2.60	±0.05	
36"x48", 36"x36"	0.093	2.363	±0.004	2.55	±0.05	
	0.125	3.175	±0.004, ±0.005	2.50, 2.55, 2.60	±0.05	
	0.187	4.750	±0.006	2.50	±0.05	
	0.250	6.350	±0.005	2.50, 2.55, 2.60	±0.05	
	0.005	0.127	±0.005	2.50, 2.55	±0.04	
	0.010	0.254	±0.001	2.45, 2.50, 2.55, 2.60	±0.04	
	0.015	0.381	±0.0015	2.45, 2.50, 2.55	±0.04	
	0.020	0.508	±0.002	2.40, 2.45, 2.50, 2.55	±0.04	
DiClad 527	0.031	0.787	±0.002	2.40, 2.45, 2.50, 2.55, 2.60	±0.04	
Master Sheet Size** :	0.040	1.016	±0.002	2.40, 2.45, 2.50, 2.55, 2.60	±0.04	
36"x48", 36"x36"	0.047	1.194	±0.002	2.50, 2.55	±0.04	
	0.060	1.524	±0.003	2.45, 2.50, 2.55	±0.04	
	0.062	1.575	±0.003	2.40, 2.45, 2.50, 2.55, 2.60	±0.04	
	0.093	2.363	±0.004	2.45, 2.55	±0.04	
	0.125	3.175	±0.005	2.45, 2.50, 2.55	±0.04	
	0.005	0.127	±0.0005	2.33	±0.02	
	0.010	0.254	±0.001	2.33	±0.02	
D:01 1000	0.015	0.381	±0.001	2.33	±0.02	
DiClad 870	0.020	0.508	±0.0015	2.33	±0.02	
Master Sheet Size** : 36"x48", 36"x36"	0.030	0.861	±0.002	2.33	±0.02	
00 X 10 , 00 X00	0.040	1.016	±0.002	2.33	±0.02	
	0.060	1.524	±0.002	2.33	±0.02	
	0.125	3.175	±0.004	2.33	±0.02	
	0.005	0.127	±0.0005	2.17, 2.20	±0.02	
	0.010	0.254	±0.001	2.17, 2.20	±0.02	
D:011 000	0.015	0.381	±0.001	2.17, 2.20	±0.02	
DiClad 880	0.020	0.508	±0.0015	2.17, 2.20	±0.02	
Master Sheet Size** : 36"x48", 36"x36"	0.030	0.762	±0.002	2.17, 2.20	±0.02	
25 7.15 , 55 7.55	0.050	1.270	±0.002	2.17, 2.20	±0.02	
	0.060	1.524	±0.002	2.17, 2.20	±0.02	
	0.125	3.175	±0.004	2.17, 2.20	±0.02	

^{**}Master Sheet Sizes are not available on all products or thicknesses. Other thickness options available. Tolerances are subject to change and custom tolerances may be available. Please contact Arlon Customer Service with questions about material availability.

CuClad® Series

Cross-plied woven fiberglass / PTFE laminates available in a range of Dk's (2.17 to 2.55) and loss (0.0009 to 0.0018). The sequential layers of fabric are cross-plied to ensure in-plane isotropy for applications requiring matched electrical properties in the X-Y plane.

	St	andard Thick	Dielectric Constant		
Product	Inches	Millimeters	Tolerance	Nominal	Tolerance
	0.004	0.102	±0.0005	2.40	±0.10
	0.010	0.245	±0.0009	2.48, 2.55	±0.04
	0.015	0.381	±0.0015	2.44, 2.48, 2.55	±0.04
	0.020	0.508	±0.002	2.45, 2.48, 2.50, 2.55	±0.04
CuClad 250GX	0.030	0.762	±0.002	2.40, 2.45, 2.50, 2.55	±0.04
Master Sheet Size** 36"x48" (non-cross-plied),	0.031	0.787	±0.002	2.45, 2.50, 2.55	±0.04
36"x36" (cross-plied)	0.047	1.194	±0.002	2.50	±0.04
	0.060	1.524	±0.002	2.40, 2.45, 2.50, 2.55	±0.04
	0.062	1.575	±0.002	2.45, 2.50, 2.55	±0.04
	0.093	2.362	±0.002	2.48	±0.04
	0.120	3.048	±0.004	2.45, 2.50, 2.55	±0.04
	0.125	3.175	±0.004	2.45, 2.50, 2.55	±0.04
	0.010	0.254	±0.001	2.50	±0.05
	0.015	0.381	±0.0015, ±0.002	2.50	±0.05
CuClad 250GT	0.020	0.508	±0.002	2.50	±0.05
(Thickness listed	0.031	0.787	±0.002	2.50	±0.05
includes copper cladding)	0.047	1.194	±0.002	2.50	±0.05
Master Sheet Size** :	0.062	1.575	±0.003	2.50	±0.05
36"x48" (non-cross-plied),	0.094	2.388	±0.004	2.50	±0.05
36"x36" (cross-plied)	0.125	3.175	±0.005	2.50	±0.05
	0.187	4.750	±0.006	2.50	±0.05
	0.250	6.350	±0.006	2.50	±0.05
	0.005	0.127	±0.0005	2.33	±0.04
CuClad 233GY & 233LX	0.010	0.254	±0.001	2.33	±0.04
Master Sheet Size** :	0.015	0.381	0.0015	2.33	±0.02
GY - 36"x48"(non-cross plied),	0.020	0.508	0.0015	2.33	±0.02
36"x36" (cross-plied) LX - 34"x48"(non-cross plied),	0.031	0.787	0.002	2.33	±0.02
34"x36" (cross-plied)	0.045	1.143	0.002	2.33	±0.02
(LX represents a premium grade with additional testing)	0.062	1.575	0.002	2.33	±0.02
with additional toothing,	0.125	3.175	0.004	2.33	±0.02
	0.005	0.127	0.0005	2.17	±0.04
	0.010	0.254	0.001	2.17, 2.20	±0.04
CuClad 217GY & 217LX	0.015	0.381	0.0015	2.17	±0.02
Master Sheet Size** :	0.020	0.508	0.002	2.17	±0.02
GY - 36"x48"(non-cross plied),	0.025	0.635	0.002	2.17	±0.02
36"x36" (cross-plied) LX - 34"x48"(non-cross plied),	0.031	0.787	0.002	2.17	±0.02
34"x36" (cross-plied)	0.040	1.016	0.002	2.17, 2.20	±0.02
(LX represents a premium grade with additional testing	0.045	1.143	0.002	2.17	±0.02
and certificate of analysis)	0.060	1.524	0.002	2.17	±0.02
	0.062	1.575	0.002	2.17	±0.02
	0.125	3.175	0.004	2.17	±0.02

^{**}Master Sheet Sizes are not available on all products or thicknesses. Other thickness options available. Tolerances are subject to change and custom tolerances may be available. Please contact Arlon Customer Service with questions about material availability.

CuClad® Series

Cross-plied woven fiberglass / PTFE laminates available in a range of Dk's (2.17 to 2.55) and loss (0.0009 to 0.0018). The sequential layers of fabric are cross-plied to ensure in-plane isotropy for applications requiring matched electrical properties in the X-Y plane.

Product		Standard Thi	ckness	Dielectric Constant		
Product	Inches	Millimeters	Tolerance	Nominal	Tolerance	
	0.0053	0.135	±0.0005	2.53	±0.10	
CuClad 250LX	0.0101	0.257	±0.0009	2.48, 2.55	±0.04	
Master Sheet Size**	0.0147	0.373	±0.0015	2.44, 2.55	±0.04	
0.411 4011 (0.0193	0.490	±0.002	2.43	±0.04	
34"x48" (non-cross-plied), 34"x36" (cross-plied)	0.030	0.762	±0.002	2.45, 2.50, 2.55	±0.04	
or xoo (cross piloa)	0.031	0.787	±0.002	2.45	±0.04	
(LX represents a premium grade with additional testing	0.060	1.524	±0.002	2.41, 2.42, 2.43, 2.45, 2.50, 2.55	±0.04	
and certificate of analysis)	0.0625	1.588	±0.002	2.50, 2.55	±0.04	
	0.090	2.286	±0.003	2.50	±0.04	
	0.125	3.175	±0.004	2.45, 2.50, 2.55	±0.04	

IsoClad® Series

Non-woven fiberglass / PTFE laminates available in a of Dk's of either 2.17 or 2.33 with a loss tangent of 0.0013 or 0.0016 respectively. These materials offer lower modulus permitting a more flexible thin laminate than is typical with a woven glass reinforced product.

Durchurt	St	Standard Thickness		Dielectric Constant	
Product	Inches	Millimeters	Tolerance	Nominal	Tolerance
	0.005	0.127	±0.0007	2.33	±0.04
	0.010	0.254	±0.001	2.33	±0.04
IsoClad 933	0.015	0.381	±0.0015	2.33	±0.04
Master Sheet Size**	0.020	0.508	±0.002	2.33	±0.04
36"x48"	0.031	0.787	±0.002	2.33	±0.04
	0.045	1.143	±0.003	2.33	±0.04
	0.060	1.524	±0.004	2.33	±0.04
	0.005	0.127	±0.0005	2.17	±0.02
	0.010	0.254	±0.001	2.17	±0.02
IsoClad 917	0.015	0.381	±0.0015	2.17	±0.02
Master Sheet Size**	0.020	0.508	±0.002	2.17	±0.02
36"x48"	0.031	0.787	±0.002	2.17	±0.02
	0.045	1.143	±0.003	2.17	±0.02
	0.062	1.575	±0.003	2.17	±0.02

AR Series (Legacy Material)

Glass / PTFE laminates with or without micro-dispersed ceramic fillers. These Legacy products continue to be manufactured to support legacy customer designs. Arlon encourages new designs and inquiries towards AD1000 over AR1000. The newer products offer both lower price as well as higher performance to provide more Customer Value.

Product	Standard Thickness		Nominal Dielectric
Product	Inches	Millimeters	Constant
	0.024	0.610	9.7
AR1000	0.031	0.787	9.7
Master Sheet Size**:	0.062	1.575	9.8
36"x48"	0.093	2.362	9.8

25 Series, Non-PTFE, Low Loss Thermoset Resin Systems

The 25 Series Products are Ceramic Hydrocarbon, Low Loss Thermoset material family with matching Pre-pregs. Excellent for multi-layer applications. 25FR contains a Flame Retardant and is UL-94V0.

Standard Laminate Thickness (inches)			
25N	25FR	Tolerance	
0.006	0.006	0.0007	
0.008	0.008	0.0010	
0.010	0.010	0.0010	
0.012	0.012	0.0015	
0.018	0.018	0.0020	
0.020	0.020	0.0020	
0.024	0.024	0.0020	
0.030	0.030	0.0030	
0.060	0.058	0.0040	

Prepreg Thickness (inches)			
Glass Style	25N	25FR	
1080	0.0039	0.0039	
2112	0.0058	0.0058	
2113	0.0067	0.0067	

Multiclad HF -

Non-PTFE, Halogen-Free, Low-Loss Thermoset resin system - High Tg, UL-94V0 material excellent for high reliability, high frequency multilayer applications.

Standard Laminate Thickness			
Inches	Tolerance		
0.003	±0.007		
0.004	±0.007		
0.005	±0.007		
0.006	±0.007		
0.008	0.0010		
0.010	0.0010		
0.020	0.0020		
0.030	0.0030		
0.060	0.0040		

Prepreg Thickness (inches)		
Glass Style	Tolerance	
104	0.003	
106	0.004	
1080	0.005 & 0.006	

www.atechcircuit.com

Copper Cladding

Arlon offers a variety of copper foil cladding for high performance laminates to insure the optimal balance of low insertion loss, excellent mechanical properties and cost. Below is a list of typical copper foil options.

Common Fail		Typical Surface Roughness (root mean squared, R _{rms})	
Copper Foil	Treated Side µin (µm)	Untreated Side µin (µm)	mil (mm)
1/2 oz Electrodeposited (ED) Copper	31 (0.78)	10-15 (0.3-0.4)	0.7 (0.018)
1 oz Electrodeposited (ED) Copper	46 (1.2)	10-15 (0.3-0.4)	1.4 (0.036)
2 oz Electrodeposited (ED) Copper	82 (2.1)	10-15 (0.3-0.4)	2.8 (0.072)
1/2 oz Reverse Treat Electrodeposited (RT)	13 (0.3)	20-40 (0.5-1.1)	0.7 (0.018)
1 oz Reverse Treat Electrodeposited (RT)	17 (0.43)	20-40 (0.5-1.1)	1.4 (0.036)
1/2 oz Rolled Copper (RA)	30 (0.78)	5-12 (0.13-0.3)	0.7 (0.018)
1 oz Rolled Copper (RA)	30 (0.78)	5-12 (0.13-0.3)	1.4 (0.036)


PIM Grade Copper available on certain products. Additional copper foils, heavy metal plate or specialty foils such as Ohmega Technologies Ohmega-Ply® or TICER TCR® Resist foils are available upon request. Not all copper foil options are available on all products or thicknesses. Please contact Arion Customer Service with questions about material availability.





Surface Roughness Profile of Arlon 0.5 Ounce, Electrodeposited (ED) Copper via Non-Contact Optical Aberration Technique


Arion Part Numbers

FOR REFERENCE ONLY. PLEASE CONTACT YOUR ARLON REPRESENTATIVE FOR ADDITIONAL PRODUCT OPTIONS, SPECIFIC DIELECTRIC DESIGNS OR REQUIREMENTS & AVAILABILITY.









Codes for Typical Copper Cladding and Panel Size

Metal Cladding Codes*		
Code	Copper Type & Weight	
1	1 oz ED	
2	2 oz ED	
3	½oz Rolled	
4	1 oz Rolled	
5	½oz ED	
7	1/2 oz Reverse Treated ED	
8	² oz Reverse Treated ED	
9	¹ oz Reverse Treated ED	
0	Unclad	

Panel Size Codes*			
Panel Size (Inches)	Panel Size (Millimeters)	Code	
18 x 24	547 x 610	001	
12 x 18	305 x 457	002	
18 x 36	457 x 915	004	
36 x 48	915 x 1220	013	
16 x 36	407 x 915	014	
24 x 36	610 x 915	057	
18 x 48	457 x 1220	072	
48 x 54	1220 x 1372	615	
24 x 54	610 x 1372	825	

^{*} Other metal cladding types and thicknesses, and panel size options are available for various products. Please contact Arlon Customer Service with questions about material availability.



Arlon Microwave Materials... Challenge Us

For samples, technical assistance, customer service or for more information, please contact Arlon Materials for Electronics Division at the following locations:

NORTH AMERICA:

Arlon LLC
Electronic Substrates
9433 Hyssop Drive
Rancho Cucamonga, CA 91730

Tel: (909) 987-9533 Fax: (909) 987-8541

Arlon LLC Microwave Materials 1100 Governor Lea Road Bear, DE 19701

Tel: (800) 635-9333 Outside U.S. & Canada: (302) 834-2100

Fax: (302) 834-2574

NORTHERN EUROPE:

Arlon LLC 44 Wilby Avenue Little Lever Bolton, Lancashire BL31QE United Kingdom

Tel: (44) 120-457-6068 Fax: (44) 120-479-6463

SOUTHERN CHINA:

Arlon LLC Room 601, Unit 1, Bldg 6 Liyuan, Xincun Shahe Shenzhen, China 518053 Tel: (86) 755-269-066-12 Fax: (86) 755-269-104-75

NORTHERN CHINA:

Arlon LLC Room 11/401, No. 8 Hong Gu Road Shanghai, China 200336 Tel/Fax: (86) 21-6209-0202

SOUTHERN EUROPE:

Arlon LLC 1 Bis Rue de la Remarde 91530 Saint Cheron, France Tel: (33) 951-096-082 Fax: (33) 164-566-489